



CZECH TECHNICAL UNIVERSITY IN PRAGUE
FACULTY OF CIVIL ENGINEERING – TEST LABORATORY
Test laboratory No. 1048 accredited by ČIA according to
ČSN EN ISO/IEC 17025:2018
Thákurova 7, 166 29 Praha 6



L 1048

EXPERT LABORATORY OL 124

Phone: +420224354806

E-mail: jiranek@fsv.cvut.cz

No. of copies: 2
Copy No: 1
No. of pages: 3
Page No.: 1
No. of annexes: 0
No. of annexes pages: 0

Order No: 8602077A000

TEST REPORT No: 124006/2021

upon the test : **Determination of the radon diffusion coefficient of the BAUDICHT XL A membrane carried out in accordance with the ISO/TS 11665-13**

Client's name and address:

HANSE BAUSTOFFE
Handelsges. mbH & Co. KG
Lily-Braun-Straße 44 - 46
23843 Bad Oldesloe
Germany

Date of issue: 20.1.2021

Approved by:



.....
prof. Ing. Martin Jiránek, CSc.
head of OL 124 laboratory

This report can only be reproduced in its entirety; in part only with a written consent of the testing laboratory. The test results refer exclusively to the subject of the test (test sample).

Subject of the test: Baudicht XL A – EPDM membrane

Testing procedure: Determination of the radon diffusion coefficient

Test regulation: ISO/TS 11665-13, method A

Test execution date: 14.1.2021 – 20.1.2021

Test execution place: laboratory OL124 – D2044d

Duration of the decisive measurement: 114 hours

Test samples

Test samples were cut from the material handed by the client representative Dipl. Ing. O. Otte on 10.12.2020. The samples were registered with marks 40/20/J (1 to 5) by M. Jiránek. The dimensions of the samples were 135 x 325 mm (effective area $293 \cdot 10^{-4} \text{ m}^2$) and their thickness was 1,23 mm. The tested joint was sealed with a 150 mm wide one-sided adhesive tape.

Test method

Radon diffusion coefficient was determined according to the method A of ISO/TS 11665-13. The tested samples were placed between the source and the receiver containers. Radon diffuses through the samples from the source container, which is connected to the radon source RF 100, to the receiver containers. Concentrations on both sides of the tested samples are measured continuously by radon detectors TSR-4 of the TERA system (receiver containers) and current mode ionization chambers (source container). Radon diffusion coefficient was derived from the process of fitting the numerical solution to the curves of radon concentration measured in the receiver containers. Numerical solution is based on the one-dimensional time-dependent diffusion equation describing radon transport through the tested material.

Laboratory conditions

Baudicht XL A – material

Steady state radon concentration in the source container: $1,7 \pm 0,1 \text{ MBq/m}^3$

Maximum radon concentration in the receiver containers: $165,0 \pm 1,0 \text{ kBq/m}^3$

Baudicht XL A – joint

Steady state radon concentration in the source container: $1,7 \pm 0,1 \text{ MBq/m}^3$

Maximum radon concentration in the receiver containers: $49,4 \pm 0,4 \text{ kBq/m}^3$

Laboratory temperature: $22^\circ\text{C} \pm 1^\circ\text{C}$

Relative humidity of air in the laboratory: $39\% \pm 3\%$

Pressure difference between the lower and the upper containers: $1 \text{ Pa} \pm 1 \text{ Pa}$

Test device

Radon detectors TSR-4 of the TERA system (N17)
 Measuring system with ionization chambers operating in current mode (N14)
 Radon concentration measuring system RM-2 (N15)
 Micrometer (N11)

Test results

The resulting values of the radon diffusion coefficient, the radon diffusion length and the radon resistance including expanded measurement uncertainty, are listed in the following table. The results refer to the samples as they were taken over.

TESTED MATERIAL		Baudicht XL A	Baudicht XL A, joint
RN DIFFUSION COEFFICIENT D (m^2/s)	mean value	$4,8 \cdot 10^{-11}$	$1,4 \cdot 10^{-11}$
	$\pm U$	$\pm 0,6 \cdot 10^{-11}$	$\pm 0,2 \cdot 10^{-11}$
RN DIFFUSION LENGTH l (m)	mean value	$4,8 \cdot 10^{-3}$	$2,6 \cdot 10^{-3}$
	$\pm U$	$\pm 0,6 \cdot 10^{-3}$	$\pm 0,3 \cdot 10^{-3}$
RN RESISTANCE R_{Rn} (Ms/m)	mean value	26	91
	$\pm U$	± 3	± 11

The expanded uncertainties of measurement $\pm U$ mentioned are the product of standard measurement uncertainties and the expansion coefficient $k = 2$, which provides a confidence interval of approx. 95 %. The radon diffusion length was calculated according to the equation $l = \sqrt{D/\lambda}$ and the radon resistance as follows: $R_{Rn} = \frac{\sinh(d/l)}{\lambda \cdot l}$, where $\lambda = 2,1 \cdot 10^{-6} s^{-1}$ and $d = 1,23 \text{ mm} = 1,23 \cdot 10^{-3} \text{ m}$.

The test was performed by: prof. Ing. Martin Jiránek, CSc., Ing. Veronika Kačmaříková, Ph.D.

The report was prepared by: prof. Ing. Martin Jiránek, CSc.